

AS1810 (ESP411) 1 Part neutral thixotropic adhesive sealant

Introduction

AS1810 is a non-corrosive, 1-part, room temperature vulcanising (RTV) silicone rubber. It is one of a new family of products called acetone cure sealants that are solvent free. It exhibits excellent primerless adhesion to many substrates. The product is cured rapidly in contact with atmospheric moisture to a tough rubber. It does not corrode copper or its alloys and exhibits excellent primerless adhesion when fully cured. ACC employed MERL (Materials Engineering Research Laboratories) to carry out extensive testing using Liquid F diesel (ISO1817) and RME diesel (DIN EN 14214) a full copy of the report is available on request.

Key Features

- **Non-Corrosive**
- **Excellent Adhesion**
- **Improved fuel resistance**
- **Cure through to 3 mm in 24 hours**

How to Use

AS1810 is ready for use. If supplied in cartridges it can be applied using either manual or pneumatic dispensers. It can also be applied from bulk containers using conventional drum dispensing equipment.

Application and Cure

All surfaces to which the sealant is to be applied should be clean, dry and free from grease, dirt, and loose material. Priming of surfaces is not normally required. If using as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within 15 to 20 seconds. For optimum bond strength the thickness of the sealant joint is 1 to 2mm. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days.

Health and Safety - Material Safety Data Sheets available on request.

Packages - 75 ml and 310 ml cartridges. Arrangements can be made to supply in bulk containers.

Storage and Shelf Life – Expected to be 12 months in cartridges and 9 months in bulk, unopened containers.

Property

Uncured Product

Property	Test Method	Value
Colour:		Black Paste
Appearance:		4 minutes *
Tack Free Time:		<24 hours *
3mm Cure Through:		169g / minute
Extrusion Rate:		mPas
Viscosity		
* measured at 23+/-2°C and 65% relative humidity.		

Cured Elastomer

(after 7 days cure at 23+/-2°C and 65% relative humidity)

Tensile Strength:	BS903 Part A2	1.81 MPa
Elongation at Break:	BS903 Part A2	353 %
Youngs Modulus:		
Modulus at 100% Strain:	BS903 Part A2	0.80 MPa
Tear Strength:	BS903 Part A3	6.00 kN/m
Hardness:	ASTM D 2240-95	35° Shore A
Specific Gravity:	BS 903 Part A1	1.05
Linear Shrinkage:		0.40%
Thermal Conductivity:		0.19W/mK
Coefficient of Thermal Expansion:		
Volumetric		884 ppm / °C
Linear		295 ppm / °C
Min. Service Temperature:		-50°C
Max. Service Temperature:	AFS 1540B	220 °C

Electrical Properties

Volume Resistivity:	ASTM D-257	6.38E+14Ω.cm
Surface Resistivity:	ASTM D-257	3.3E+12Ω
Dielectric Strength:	ASTM D-149	>20kV/mm
Dielectric Constant at 1MHz:	ASTM D-150	2.97
Dissipation Factor at 1MHz:	ASTM D-150	2.5E-3

Adhesion Testing

Overlap Shear Strength:	ASTM D 1002	kg/cm²
Copper		4.87
Aluminium		6.94
Stainless Steel 304		
Polycarbonate		

Customers are advised to carry out their own tests on clean, degreased substrates to ensure satisfactory adhesion is achieved

Stress cracking can appear on some grades of polycarbonate. Customers are advised to carry out initial testing to ensure product compatibility.

All values are typical and should not be accepted as a specification.

Revision date: 29/09/2008

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.