

AS1420

SILCOTHERM 1 Part flowable heat cured silicone adhesive sealant

Introduction

This is a heat cured, non-corrosive, neutral cure, 1-part, silicone adhesive sealant. It is one in a range of Addition cure products which are solvent free. It exhibits primerless adhesion to many substrates when cured at temperatures above 100°C. It cures to form a very tough resilient silicone elastomer. This product will not corrode copper or its alloys and is suitable for use with electronic components.

Key Features

- Fast cure with heat
- Excellent thermal conductivity
- Non-corrosive
- Tough protective rubber

Use and Cure Information

This product is a ready to use 1-Part system. It is recommended that liquid versions be thoroughly mixed prior to use, particularly thermally conductive products which are supplied in tubs or pails. Ensure that all surfaces of the substrate are clean and degreased. The work area should be free of contaminants such as organic compounds of sulphur, phosphorus, nitrogen and tin, which act as catalyst poisons.

The rate of cure will depend on how long it takes for the sealant to reach the required curing temperature. Small beads of 1 to 2mm diameter, used as formed-in-place gaskets, can be cured quickly with hot air guns e.g. paint stripper types. With larger sections of sealant or when using as an encapsulant, cure times will increase and the use of an oven will be needed. Increasing the temperature will reduce cure times and maximum cure temperature should not exceed 200°C. All times are based on the actual time in an air-circulating oven at the stated temperature. Note: Improved adhesion is achieved by post cure at 120 to 150°C for 1 to 2 hours.

“For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality”

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Adhesives are available in a variety packaging including cartridges and bulk containers. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 31/07/2019

Property	Test Method	Value
Uncured product		
Appearance		Grey viscous liquid
Cure Type		Addition
FDA	CFR (21) 177.2600	No
Max Cure Mins @ 100 °C		30 mins
Rheology		Flowable
Self Bonding		Yes
Viscosity A-Part mPas	Brookfield	43000 mPas
Cured product		
After 1 hour at 150°C		
CTE Linear ppm/°C		187 ppm/°C
CTE Volumetric ppm/°C		562 ppm/°C
Colour		Grey
Duro Shore A	ASTM D 2240-95	67
Elongation %	ISO 37	70 %
Linear Shrinkage %		2 %
Max Working Temp +°C	AFS_1540B	260 °C
Min Working Temp - °C		-50 °C
SG	BS ISO 2781	2.06
Tensile MPa	ISO 37	3.1 MPa
Thermal Conductivity W/mK		1.38 W/mK
UL 94V-0		No
Storage		
Max storage temperature °C		15 °C
Min storage temperature °C		-5 °C
Shelf life		6 mths
Electrical properties		
Dielectric Constant @ 1kHz	ASTM D-150	6
Dielectric Strength kV/mm	ASTM D-149	22.5 kV/mm
Surface Resistivity ohms	ASTM D-257	1.3E+15 ohms
Volume Resistivity ohms cm	ASTM D-257	7.7E+15 ohms cm

The information and recommendations in this publication are to the best of our knowledge reliable. However, nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed. All values are typical and should not be accepted as a specification