

**Protac**<sup>®</sup>

Engineering Adhesives, Industrial Sealants

TECHNICAL DATA SHEET

Revision number: 50211

Protac 2822

### Protac 2822 Screw Lock

**Product description**

Protac 2822 Screw Lock is a fast cure, low strength anaerobic threadlocker. The product cures when confined in the absence of air on close-fitting metal surfaces.

**Specification**

Meets Military specifications: MIL-S-46163 Type II Grade M.

**Typical applications**

Protac 2822 is formulated to lock all metric and imperial nuts and screws, preventing vibration loosening and leakage through the threads. Protac 2822 is slightly oil tolerant, so it will bond some 'as received' parts, but best results are obtained with clean substrates. The thixotropic nature of the product prevents run off, dripping and migration after assembly. Protac 2822 is typically used on mounting housing screws. Protac 2822 prevents corrosion of assembled parts.

**Properties of material**

Chemical type	Di-Methacrylate
Appearance	Purple
Specific Gravity	1.05
Viscosity cPs <sup>1</sup>	1,200
Viscosity cPs <sup>2</sup>	5,000
Breakaway Torque (N.m) <sup>3</sup>	4 -7
Typical	6
Prevailing Torque (N.m) <sup>3</sup>	2 - 8
Typical	4
Fixture Time <sup>4</sup>	≤15
Full Cure @20°C (hours)	24
Flash Point (°C)	>100
Shelf Life @ 20°C (months)	24
Max Gap Fill (mm)	0.25
Operating Temp Range (°C)	-50 to +150

1 Brookfield RVT, spindle 3, 20rpm

3 On M10 black oxide steel bolt and M10 bright steel nut, ISO10964

4 ISO 10964

Typical curing speed, % of final strength:-

15 mins Finger tight

1 hour~ 70% strength


24 hours 100% strength

**Cure speed vs. substrate**

Cure speed and strength vary according to the substrates. When used on mild steel and brass components anaerobic adhesives will reach full cure faster than more inert materials such as stainless steel and zinc dichromate. Protac AC32 activator may be used to accelerate cure speed

**Cure speed vs. bond gap**

The size of the bond gap greatly affects the speed of cure of anaerobic adhesives. Bond gap varies with thread type and size of the fastener.



**Protac**<sup>®</sup>

Engineering Adhesives, Industrial Sealants

TECHNICAL DATA SHEET

Revision number: 50211

Protac 2822

The larger the gap between threads, the slower the cure speed.  
Maximum recommended gap for 2822 is 0.25mm

**Cure speed vs. temperature**

All figures relating to cure speed are tested at 22°C. Lower temperatures will result in slower cure. Heating the assembled parts accelerates the curing process. Activator AC32 should be used when the temperature is less than 5°C.

**Typical environmental resistance**

**Hot strength**

Protac 2822 is suitable for use at temperatures up to 150°C. At 130°C the bond strength will be ~30% of the strength at 21°C.

**Heat ageing**

Protac 2822 retains ~90% full strength when heated to 100°C for 90 days then cooled and tested at 22°C.

**Chemical / Solvent Resistance**

Protac anaerobics exhibit excellent chemical resistance to most oils and solvents including motor oil, leaded petrol, brake fluid, acetone, ethanol, propanol and water. Anaerobic adhesives are not recommended for use in pure oxygen or chlorine lines.

**Chemical**

**Temp.**

**% Initial Strength Retained**

500 hours

1000 hours

Acetone

22°C

100

80

Ethanol

22°C

100

100

Motor Oil

125°C

100

100

Petrol

22°C

100

100

Brake Fluid

22°C

100

100

Water/Glycol

87°C

90

85

**General information**

For safe handling of this product consult the Material Safety Data Sheet.

Anaerobic adhesives only cure in the absence of air and with metal part activation. Adhesive outside the joint will remain uncured and may be wiped away with a cloth.


Protac 2822 is suitable for most medium and coarse- threaded screws. Not recommended on certain plastics as stress cracking can sometimes result. Some anti-corrosion chemicals inhibit the cure system in this type of anaerobic. Trials are recommended to establish whether cleaning of the parts is necessary. AC32 Activator may be required on plated parts.

**Directions for use**

Ensure parts are clean, dry and free from oil and grease. Apply adhesive to all engaged threads. Assemble parts and allow to cure. Wipe excess adhesive from outside of joint.

**Storage**

Store in a cool area out of direct sunlight. Refrigeration to 5°C gives optimum storage stability.



**Protac**<sup>®</sup>

Engineering Adhesives, Industrial Sealants

TECHNICAL DATA SHEET

Revision number: 50211

Protac 2822

---

<b>Packaging</b>	Bottles: 50ml and 250ml. Available in bulk for use with dispensing systems.
<b>Data ranges</b>	The data contained in this data sheet may be reported as typical value and/or range. Values are based on actual test data and are verified on a regular basis.
<b>Notes</b>	The information contained herein is produced in good faith and is believed to be reliable but is for guidance only. Novachem Ltd. and its agents cannot assume liability or responsibility for results obtained in the use of its product by persons whose methods are outside or beyond our control. It is the user's responsibility to determine the suitability of any of the products and methods of use or preparation prior to use mentioned in our literature and furthermore the user's responsibility to observe and adapt such precautions as may be advisable for the protection of personnel and property in the handling and use of any of our products.