


SILICONE GAP FILLER PAD TEL-ZS-SI

soft, highly thermally conductive elastomer / Low Volatile Siloxanes (LV)



TEL-ZS-SI is a non dielectric high performance thermally conductive LV silicone foil for an optimised thermal coupling between electronic packages and heat sinks even over large gaps or big tolerances. Through the specific formulation and filling an extraordinary high anisotropic thermal conductivity is reached. Its conformal surface structure and high softness guarantee a very good compliance to the contact surfaces at low pressure. Thus the total thermal resistance is minimised.



Release 02 / 2021

PROPERTIES

- High surface compliance and softness
- Low volatile siloxane content (LV)
- Non dielectric
- Thermal conductivity: 20 W/mK (anisotropic)
- Extraordinary chemical resistance and longterm stability
- Shock absorbing

AVAILABILITY

- Sheet 120 x 120 mm (TEL-ZSXXXX-SI)
- Die cut parts
- Optional with adhesive stripes or dots (TEL-ZSXXXX-SI-A1)

APPLICATION EXAMPLES

Thermal link of:

- MOSFETs or IGBTs
- Power diodes or AC/DC converters
- Power modules

For use in Switch mode power supplies / Motor control units / Automotive engine management systems / UPS units / Solar systems



Technical Data Sheet

PROPERTY	UNIT	TEL-ZS0200-SI	TEL-ZS0500-SI
MATERIAL			
		Carbon filled silicone elastomere	Carbon filled silicone elastomere
Colour		Black	Black
Thickness	mm	0.2 ±0.05	0.5 ±0.05
Hardness	Shore 00	60	60
Flammability (Equivalent)	UL 94	V0	V0
RoHS Conformity	2015 / 863 / EU	Yes	Yes
THERMAL			
Resistance ¹ @ 35 PSI @ Thickness	°C-inch ² /W (mm)	0.007 (0.17)	0.018 (0.44)
Resistance ¹ @ 15 PSI @ Thickness	°C-inch ² /W (mm)	0.017 (0.18)	0.027 (0.48)
Resistance ¹ @ 7 PSI @ Thickness	°C-inch ² /W (mm)	0.030 (0.19)	0.042 (0.49)
Thermal Conductivity ¹	W/mK	20	20
Operating Temperature Range	°C	- 40 to + 150	- 40 to + 150
ELECTRICAL			
Volume Resistivity	Ohm - cm	< 50,000	< 50,000

Test Methods: ¹ASTM D 5470. All data without warranty and subject to change. Please contact us for further data and information.
Shelf life adhesive: 6 months when stored in original packaging at room temperature and 50% relative humidity.

Thicknesses: 0.2 mm / 0.3 mm / 0.5 mm

mm vs. N/cm² (PSI) / Rth vs. N/cm² (PSI)



All technical data and information are without warranty and believed to be reliable and accurate, corresponding to the latest state of the art. Since the products are not provided to conform with mutually agreed specifications and their use and processing are unknown we cannot guarantee results, freedom from patent infringement, or their suitability for any application. Product testing by the applicant is recommended. We reserve the right of changes.