

Transparency

Resin 8806/30 (ex LD 44 5%) + Hardener (ex 3000)

- 2-components polyurethane casting resin
- solvent-free system
- opaque, translucent and UV-resistant
- semi-hard curing degree
- excellent adhesive properties
- ideal for LED applications
- **TIP: good combination possibilities with kisling's crystal clear and thermal conductive casting resins**

Product specification:

Mixing ratio (weight):	Resin 8806	100 parts
	Hardener 8930	100 parts
Viscosity (22°C):	Resin 8806	850 – 950 mPa·s
	Hardener 8930	450 – 750 mPa·s
	Mixing viscosity	650 – 850 mPa·s
Density (22°C):	Resin 8806	1.05 – 1.10 g/cm ³
	Hardener 8930	1.10 – 1.15 g/cm ³
Colour:	White translucent / opaque (depends on the thickness)	
Turbidity level:	5%	
Pot life:	30 – 45 minutes	
	The curing time depends on the thickness of the layer, the casting volume and the temperature.	
Curing time (22°C):	16 – 30 hours	
Final hardness	10 – 14 days	

Physical properties:

Shore-Hardness:	A 60 – 70	ISO 868, DIN 53505
Thermal conductivity:	0.2 W/(m·K)	DIN EN ISO 22007
Glass transition temperature:	3.0°C	TMA
Coefficient of expansion:		< T _g , TMA > T _g , TMA
Shrinkage after curing:	<1 %	
Water absorption:	0.2 % (30 days at 23°C)	
Insulation class:	B	IEC 60085
Operating temperature:	-40°C up to +130°C no affect of the physical properties -40°C up to + 90°C no affect of the optical properties	

Shelf life:	6 months in sealed original containers when stored in dry conditions (15°C to 25°C).
Packaging:	Resin and hardener are offered in separate packaging units.
RoHS:	We hereby certify that all products are unexceptional RoHS conform according to the EU-directive 2011/65/EG (RoHS2) and the amendment of Directive 2015/863.

TDS_8806_30+8930_e/PC/25.11.2022